


Diarylide Yellow AAOA

Color Type Disazo
Color Index No. P.Y. 17
CAS NO. 4531-49-1
Structure:



Description:

- More greenish and better light resistance than yellow 12 and 14.
- S1701 greenish high transparent, recommend using for solvent-based ink: PA, CLPP resin.
- P1702 is economic transparent medium tone, recommend using for polyolefin, PVC.
- P1703 is high color strength can be used for offset ink, textile printing paste and plastic.

Physical properties and Fastness:

Density (g/cm ³)	1.30-1.55
Oil absorption (ml/100g)	45±5
Water soluble matter (%)	≤2.5
PH Value	6.0-7.5
Heat Resistance (°C)	180°C
Light Fastness	6
Water Resistance	5
Oil Resistance	5
Acid Resistance	5
Alkali Resistance	5
Alcohol Resistance	5
Migration	4

Color card:



Applications:

Inks	Offset Ink	●
	Solvent Based Ink	○
Plastic	Masterbatch/plastic	●
Paint	Textile Paste	○

Remark: ● High Recommendation;

○ Recommendation; -Limit Suitability

Storage conditions:

Should be sealed for avoiding light and moisture.

Package:

25kgs/20kgs craft bag with Carton box on pallet.

Please note: *** This technical index and recommending application information is based on the present knowledge for reference only. Necessary test is needed before you put into use. *******